



RENOLIT

*Rely on it.*

RENOLIT ALKORPLAN  
Metallics Silver



EXCELLENCE  
IN ROOFING



# Mechanically fastened system

## PRODUCT INFORMATION

### RENOLIT ALKORPLAN F<sub>35176</sub>

Laminated membrane of flexible PVC with woven polyester reinforcing. Conforms to UEAtc guidelines. Available in copper and silver colour. Solvent welding is not allowed.

CE conformity. Certificates are available on our website [www.renolit.com/roofing](http://www.renolit.com/roofing)

Product data	Method	Requirements according to UEAtc	Average production values RENOLIT ALKORPLAN F <sub>35176</sub> 1.5 mm	Units
Tensile strength	EN 12311-2 (A)	L ≥ 800	1298	N/50 mm
		T ≥ 800	1199	N/50 mm
Elongation at break	EN 12311-2 (A)	L ≥ 15	19	%
		T ≥ 15	19	%
Dimensional stability (6h at 80 °C)	EN 1107-2	L ≤ 0,5	-0,18	%
		T ≤ 0,5	-0,03	%
Cold crack temperature	EN 495-5	-25	-25	°C
Tear strength	EN 12310-1	L ≥ 150	535	N
		T ≥ 150	583	N
Lamination strength	EN 12316-2	≥ 80	143	N/50 mm
Vapour diffusion resistance (μ)	EN 1931	-	20 000	-
Resistance to static perforation	EN 12730	-	20	kg

Size/Weight	Thickness	Width	Weight	Roll length	Roll weight
RENOLIT ALKORPLAN F <sub>35176</sub>	1.5 mm	1.05 m	1.95 kg/m <sup>2</sup>	20 lm	ca. 41 kg

Standard conditions of sale are included in price lists, all sales of RENOLIT products are made under these conditions. RENOLIT ALKORPLAN is delivered in rolls. Every delivery may contain up to 10% of short rolls (minimum length: 8 m).

### Storage

Store dry. Rolls to be parallel and in original packing where possible, do not stack in cross form or under pressure.



*Rely on it.*



DIRECTION GÉNÉRALE  
Jonquet Face MTN Internet  
Tél.: (+229) 21 33 33 48  
95 96 00 08

04 B P : 0526 Cotonou  
contact@hpbbenin.com  
www.hpbbenin.com

DIRECTION COMMERCIALE  
HBP New City  
Mars Millaire à côté de Toxi Lobo  
Tél.: (+229) 21 32 48 48  
95 02 72 72 - 94 00 61 61