

### Description:

RELAIS consists of an acrylic texture coating system that is trowel-applied in interiors and exteriors. It is composed of vinyl resins and selectively graded aggregates and additives. Highly decorative system available in two particle sizes: Thickness F: approx. 1 mm. Thickness G: approx. 2 mm.

### Uses:

Render for façades, courtyards, stairwells, both indoors and outdoors.

### Features & benefits:

WATERPROOFING. DURABLE. ITS COLOURS ARE STABLE TO LIGHT. EXCELLENT DECORATIVE PROPERTIES.

### Surface preparation:

The background of application must be clean, free of grease, oil or loose particles. Once the support is sound, IMPRIMAIS primer is applied.

### Application:

- Mix it manually or mechanically using a low speed mixer (400 - 500 rpm).
- Apply our primer IMPRILAIS by roller or brush.
- Let the primer dry completely.
- Apply with stainless steel trowel and then, once extended the product, when it starts to dry, work with a trowel by moving it in vertically, horizontally or in circles until producing the desired travertine or circular patterns.
- The support of application must be clean, free of grease, oil or loose particles.
- Mortars must be allowed to cure for at least 28 days.
- Do not apply when rain, freezing temperatures and other bad weatehr conditions are expected.

### TechnicalFeatures:

Density: G.F...1.9 ± 0.07 g/cm<sup>3</sup> at 20°C G.G...1.87 ± 0.05 g/cm<sup>3</sup> at 20°C  
Aspect: matt textured  
Viscosity: 48.000 ± 16.000 mPa.s  
Application temperature: 5 to 30 °C  
Drying time: 3 days at 20°C

### Coverage:

F (thin finish): 1,5 - 2 kg per m<sup>2</sup> G (thick finis): 2 - 2,5 kg per m<sup>2</sup>.

### Clean up:

Clean using large amounts of water.

### Storage:

It is recommended to store this product for 1 year at most in tightly closed original packages.

The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of it's useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.



#### PROFESSIONAL CONSTRUCTIVE SOLUTIONS

©TEAIS S.A. - All rights reserved - Avda. da Enerxía, nº 153, Pol. Ind. de Sabón - 15143 Arteixo, A Coruña  
Telf.: 981 600 966 - Fax: 981 601 508 - Email: info@teais.es



DIRECTION GÉNÉRALE  
Jonquet Face MTN Internet  
Tél.: (+229) 21 33 33 48  
95 96 00 08

04 B P : 0526 Cotenou  
contact@hbpenin.com  
www.hbpenin.com

DIRECTION COMMERCIALE  
HBP New City  
Mars Militaire à côté de Yaxi Labo  
Tél.: (+229) 21 32 48 48  
95 02 72 72 - 94 00 61 61

### Packaging:

Available in packs of:

**STANDARD F:** 25 Kg

**STANDARD G:** 25 Kg

**RUSTICO FINO:** 25 Kg

**RUSTICO GRUESO:** 25 Kg

### Health and safety advice :

S2 -- Keep out of the reach of children

S3/7 -- Keep container tightly closed in a cool place

S36/37/39 -- Wear suitable protective clothing, gloves and eye/face protection

S51 -- Use only in well-ventilated areas



The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of its useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.